



Artisan NB Range Technical Data Sheet

BRICKWORKS

| Product Range | Product Name | Swatch                                                                            | State | Length (mm) | Width (mm) | Height (mm) | Dimensional Category | Average Weight / Unit (kg) | Units per Square Metre | Pack Size | Maximum Cold Water Absorption (%) | Initial Rate of Absorption (IRA) (kg/m2 min) | Coefficient of Expansion e Factor (mm/m) | Durability Class | Liability to Efflorescence | Lime Pitting Liability | LRV  |
|---------------|--------------|-----------------------------------------------------------------------------------|-------|-------------|------------|-------------|----------------------|----------------------------|------------------------|-----------|-----------------------------------|----------------------------------------------|------------------------------------------|------------------|----------------------------|------------------------|------|
| Artisan NB    | Aurora       |  | CQLD  | 230         | 110        | 76          | DW1                  | 4.1                        | 48.5                   | 400       | 10                                | 1.0-2.5                                      | 1.2                                      | Exposure Grade   | Slight                     | Slight                 | 29.2 |
| Artisan NB    | Avalanche    |  | CQLD  | 230         | 110        | 76          | DW1                  | 4.1                        | 48.5                   | 400       | 10                                | 1.0-2.5                                      | 1.2                                      | Exposure Grade   | Slight                     | Slight                 | 44.3 |
| Artisan NB    | Tundra       |  | CQLD  | 230         | 110        | 76          | DW1                  | 4.1                        | 48.5                   | 400       | 10                                | 1.0-2.5                                      | 1.2                                      | Exposure Grade   | Slight                     | Slight                 | 24.3 |
| Artisan NB    | Wolf         |  | CQLD  | 230         | 110        | 76          | DW1                  | 4.1                        | 48.5                   | 400       | 10                                | 1.0-2.5                                      | 1.2                                      | Exposure Grade   | Slight                     | Slight                 | 19.5 |

This Data represents average results from commercial production lots.  
If specific test results are required, sample should be taken from current production lots.  
AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.