

# Traditional Range Technical Data Sheet

**BRICKWORKS**

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f <sub>uc</sub> ) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m <sup>2</sup> min)	Coefficient of Expansion Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Traditional	Acland Cream			NSW	230	110	76	DW1	4	48.5	400	>12	10	0.5-2.5	1.2	Exposure Grade	Slight	Slight	27.3
Traditional	Belmore Grey			NSW	230	110	76	DW1	4	48.5	400	>12	10	0.5-2.5	1.2	Exposure Grade	Slight	Slight	11.4
Traditional	Chapel Red			NSW	230	110	76	DW1	4	48.5	400	>12	10	0.5-2.5	1.2	Exposure Grade	Slight	Slight	9.4
Traditional	Domain Terracotta			NSW	230	110	76	DW1	4	48.5	400	>12	10	0.5-2.5	1.2	Exposure Grade	Slight	Slight	17.1
Traditional	Lygon Coffee			NSW	230	110	76	DW1	4	48.5	400	>12	10	0.5-2.5	1.2	Exposure Grade	Slight	Slight	11.6
Traditional	Spencer Tan			NSW	230	110	76	DW1	4	48.5	400	>12	10	0.5-2.5	1.2	Exposure Grade	Slight	Slight	6.8

This Data represents average results from commercial production lots.  
 If specific test results are required, sample should be taken from current production lots.  
 AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.

**NUBRİK**