

Australis Range Technical Data Sheet

BRICKWORKS

Product Range	Product Name	Dimension Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Units per Square Metre	Pack Size	Characteristic Unconfined Compressive Strength (f'uc) MPa	Maximum Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m2 min)	Coefficient of Expansion e Factor (mm/m)	Durability Class	Liability to Efflorescence	Lime Pitting Liability	LRV
Australis	Coorong			TAS	230	110	76	DW1	4	48.5	400	>15	10	0.5-2.5	1.2	Exposure Grade	Slight	Slight	28.7
Australis	Hotham Peak			TAS	230	110	76	DW1	4	48.5	400	>15	10	0.5-2.5	1.2	Exposure Grade	Slight	Slight	25.4
Australis	Murray Sunset			TAS	230	110	76	DW1	4	48.5	400	>15	10	0.5-2.5	1.2	Exposure Grade	Slight	Slight	36
Australis	Wave Rock			TAS	230	110	76	DW1	4	48.5	400	>15	10	0.5-2.5	1.2	Exposure Grade	Slight	Slight	39.1

This Data represents average results from commercial production lots.
If specific test results are required, sample should be taken from current production lots.
AUSTRALIAN STANDARD TEST METHODS AS/NSZ 4456 ARE USED AS APPLICABLE.